


MONZA AUTOMOTIVE

CONTRACT • AUTOMOTIVE • UPHOLSTERY

Natural Leather

TECHNICAL DATASHEET

	TEST PRÜFVERFAHREN PRUEBA	UNIT MASSEINHEIT UNIDAD	GUARANTEED GARANTIERT GARANTIZADA
COLOUR FASTNESS TO RUBBING DRY 2000 CYCLES ABRIEFESTIGKEIT TROCKEN 2000 ZYKLEN SOLIDEZ DEL COLOR AL FROTE SECO 2000 CICLOS	EN ISO 11640	GREY SCALE	min. 4
COLOUR FASTNESS TO RUBBING WET 300 CYCLES ABRIEFESTIGKEIT NASS 300 ZYKLEN SOLIDEZ DEL COLOR AL FROTE MOJADO 300 CICLOS	EN ISO 11640	GREY SCALE	min. 4
ABRASION RESISTANCE 500 CYCLES ABNUTZUNGSTEST SCHWEISS 500 ZYKLEN PRUEBA DE ABRASIÓN SUDOR 500 CICLOS	ISO 17076		NO DAMAGE
COLOUR FASTNESS TO ARTIFICIAL LIGHT UV-BESTÄNDIGKEIT SOLIDEZ DEL COLOR A LA LUZ ARTIFICIAL	IUF 402	BLUE SCALE	min. 4
FINISHING ADHESION DRY HAFTUNG DER OBERFLÄCHENBEHANDLUNG TROCKEN ADHERENCIA DE ACABADO A SECO	EN ISO 11644	N/cm	>= 4
FLEX RESISTANCE 25.000 CYCLES BIEGEFESTIGKEIT 25.000 ZYKLEN RESISTENCIA A LA FLEXIÓN 25.000 CICLOS	EN ISO 5402		NO DAMAGE
FLAMMABILITY BRENNVERHALTEN INFLAMABILIDAD	UNECE R118 ISO 3795 / FMVSS 302	 FIRE RETARDANT	PASS >= 100 mm/min.
TEAR STRENGTH REISSFESTIGKEIT HOSE RESISTENCIA AL DESGARRO	IUP 8	N	>= 15
AZO DYES AZOFARBSTOFFE COLORANTES AZOICOS	DIRECTIVE 2002/61/CE	< 30 ppm	ABSENT
PCP CONTENT PCP-INHALT CONTENIDO PCP		< 5 ppm	ABSENT
EUROPE BOVINE ORIGIN, CORRECTED GRAIN 1,1 - 1,3 mm THICKNESS	24h DELIVERY TIME E-STOCK SERVICE - READY TO SHIP	WE DO NOT ACCEPT RESPONSIBILITY FOR ANY DAMAGE RESULTING FROM INAPPROPRIATE USE, CHEMICAL CLEANING OR ADDITIONAL IMPREGNATION.	



www.samacitalia.com