


# SUPREME AUTOMOTIVE

CONTRACT • AUTOMOTIVE • UPHOLSTERY

## Natural Leather

### TECHNICAL DATASHEET

	TEST	UNIT	GUARANTEED
<b>COLOUR FASTNESS TO RUBBING</b>   DRY 2000 CYCLES	EN ISO 11640	GREY SCALE	min. 5
<b>COLOUR FASTNESS TO RUBBING</b>   WET 500 CYCLES			min. 5
<b>COLOUR FASTNESS TO RUBBING</b>   Ph = 8 ALCALIC	EN ISO 11640	GREY SCALE	min. 5
<b>COLOUR FASTNESS TO RUBBING</b>   Ph = 5.5 ALCALIC			min. 5
<b>COLOUR FASTNESS TO RUBBING</b>   SEA WATER	EN ISO 11640	GREY SCALE	min. 5
<b>COLOUR FASTNESS TO ARTIFICIAL LIGHT</b>	IUF 402	BLUE SCALE	min. 4
<b>FINISHING ADHESION</b>   DRY HAFTUNG DER OBERFLÄCHENBEHANDLUNG   TROCKEN ADHERENCIA DE ACABADO   A SECO	EN ISO 11644	N/cm	>= 6
<b>FLEXING ENDURANCE</b>   DRY 100.000 CYCLES	EN ISO 5402		NO DAMAGE
<b>FLEXING ENDURANCE</b>   COLD 100.000 CYCLES			NO DAMAGE AT -10°C
<b>FLAMMABILITY</b>	EN ISO 1021 part I & II BS5852 Crib 5 UNI 9175:2010 CLASSE 1 IM	 FIRE RETARDANT	PASS
<b>TABER ABRASION</b>   WET 1000 CYCLES	ISO 17076	CS-10 500g	NO DAMAGE
<b>RESISTANCE TO ABRASION</b>   MARTINDALE	ISO 12947-2		100.000 CYCLES
<b>SOILING BEHAVIOR</b>   200 CYCLES FABRIC EMPA 104	ISO 26082-1	COFFEE-RED WINE-COCA COLA BEER-OIL-ALCHOL	4
<b>STAIN RESISTANCE</b>   HAND CLEANING WITH 0,5% SODIO LAURIL ETERE SOLFATO			4/5

**LEATHER TYPE:** EUROPE BOVINE ORIGIN, VEGETAL CHROME, CORRECTED GRAIN. THICKNESS 1,2 - 1,5 mm

WE DO NOT ACCEPT RESPONSIBILITY FOR ANY DAMAGE RESULTING FROM INAPPROPRIATE USE, CHEMICAL CLEANING OR ADDITIONAL IMPREGNATION.

**APPLICATION AREA:** CONTRACT - INDOOR - OUTDOOR - NAUTICAL - AUTOMOTIVE - MEDICAL



INDOOR

CONTRACT

AUTOMOTIVE

HEALTHCARE

# SAMAC

www.samacitalia.com